

## Slip Check to AS 4586-2013 Ultramat Impressions

**Report Number: M0769**

**Report Date: 24 September 2019**

**Total Number of Pages 2**

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports


**Issued by**

Safe Environments Pty Ltd  
Unit 4, 40 Bessemer Street  
Blacktown NSW 2148

**Prepared for**

Birrus Matting Systems  
60 Gaine Road  
Dandenong South VIC 3175

**Approved by**



Dale Rowell  
Authorised Signatory

24 September 2019

# Test Report No. M0769

## Slip Resistance Classification of New Pedestrian Surface Materials

### AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Birrus Matting Systems  
 Client Address: 60 Gaine Road  
 Dandenong South VIC 3175  
 Product Manufacturer: Birrus Matting Systems  
 Product Description: Ultramat Impressions

Test conducted according to: AS 4586:2013 Appendix A  
 Modification: Tests performed perpendicular to profile at request of client  
 Location: Level 1, 420 Spencer Street, West Melbourne VIC 3003  
 Conducted by: Nasser Cura

Date:	23 September 2019	Temperature:	21°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	Perpendicular to profile		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	56	55	56	56	55

<b>Reported SRV of Sample:</b>	<b>56</b>
<b>Class:</b>	<b>P5</b>

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd