

Slip test report – For the classification of the new surface material, Ultramat Creative, Aluminium Extrusions with Custom Printed Carpet

Client: Birrus Matting Systems
60 Gains Road
Dandenong VIC 3175

Report Number: RPT-25085-6
Date of Issue: 29 August 2025

Number of Pages: 2



Issued by,
Authorised Signatory



Nasser Cura

Safetech Consult Pty Ltd
80 Dorcas Street
Southbank VIC 3006

Disclaimer: It is recommended that this report be read in conjunction with AS 4586:2013 and SA HB 198:2014. This report contains privileged and confidential information. The report shall not be reproduced unless in full and with the written approval of Safetech Consult Pty Ltd.

Test Standard: AS 4586-2013, *Slip resistance classification of new pedestrian surface materials*

Report No.: RPT-25085-6

Date of Issue: 29 August 2025

Test conducted for:

Birrus Matting Systems
 60 Gains Road
 Dandenong VIC 3175

Test conducted at:

80 Dorcas Street
 Southbank VIC 3006

Test conducted by:

Safetech Consult Pty Ltd
 80 Dorcas Street
 Southbank VIC 3006
 Personnel: Nasser Cura
 Date of Test: 29 August 2025

Materials:


Product Description: Ultramat Creative, Aluminium Extrusions with Custom Printed Carpet
 Product Manufacturer: Birrus Matting Systems
 Type of Surface: Matting
 Surface Details: Unfixed
 Equipment: British Pendulum (Munro) – SN# 2444
 Slider used for Test: Slider 96 – Batch# 33

Methodology:

Method: AS 4586:2013, Appendix A (Wet Pendulum Test)
 Ambient Temperature: 21 °C
 Slider Conditioning: P400 conditioning paper, followed by Imperial Pink Lapping Film 261X 3 MIC
 Site Conditions: N/A
 Extent and Type of Cleaning Performed: None
 Direction of Test: Approximately 90° to profile (at the request of Birrus Matting Systems)
 Slope: Level surface (< 2.0 %)
 Sampling Procedure: Tested as received, sampling performed by client

Results:

Specimen #	Pendulum Operation (individual swing results)								Mean BPN
1	54	55	54	55	55	-	-	-	55
2	54	54	54	53	54	-	-	-	54
3	55	54	54	53	54	-	-	-	54
4	54	54	53	53	54	-	-	-	53
5	55	54	54	53	53	-	-	-	53
SRV (Slip Resistant Value) of the Sample:									54
Classification achieved:									P4



The reported results include an expanded uncertainty, U_{95} , calculated at a 95% confidence level using a coverage factor, $k \approx 2.0$ (excluding sampling variability). The U_{95} has been estimated to be ± 4 BPN. Assessments have been conducted on a defined, homogeneous material, with results only relating to the item(s) specifically tested.

Disclaimer: It is recommended that this report be read in conjunction with AS 4586:2013 and SA HB 198:2014. This report contains privileged and confidential information. The report shall not be reproduced unless in full and with the written approval of Safetech Consult Pty Ltd. Safetech Consult Pty Ltd (and its employees) accepts no civil liability (in any way whatsoever), for any loss or damage that may arise because of the assessments conducted, and/ or the publication of this, and any accompanied report.